

- Industrial and mobile equipment hydraulic systems operating at high pressures and temperatures in critical applications
- Hydraulic systems subject to deposit build-up such as sophisticated Computer Numerically Controlled (CNC) machines, particularly where close clearance servo-valves are used
- Systems where cold start-up and high operating temperatures are typical
- Systems requiring a high degree of load-carrying capability and anti-wear protection
- Machines employing a wide range of components using various metallurgy

Specifications and Approvals

This product has the following approvals:	15	22	32	46	68	100	150		
ARBURG Hydraulic Fluid				X					
BoschRexroth Fluid Rating List 90245			X	X	X				
DENISON HF-0			X	X	X				
FRANK MOHN Framo Hydraulic Cargo Pumping System				X					
Fives Cincinnati P-69					X				
Fives Cincinnati P-70				X					
HOCNF Norway-NEMS, Black	X	X	X	X	X	X	X		
ORTLINGHAUS-WERKE GMBH ON 9.2.10				X	X	X	X		
STROMAG AG TM-000 327					X				
This product is recommended for use in applications requiring:			15	22	32	46	68	100	150
EATON VICKERS 694 (encompasses former I-286-S, M-2950-S, or M-2952-S)					X	X	X		

This product meets or exceeds the requirements of:	15	22	32	46	68	100	150
DIN 51524-2:2006-09	X	X	X	X	X	X	X
DIN 51524-3:2006-09	X	X	X	X	X		
ISO L-HV (ISO 11158:1997)	X	X	X	X	X		
JCMAS HK VG32W			X				
JCMAS HK VG46W				X			
KRAUSS-MAFFEI Hydraulic Oil				X			
VN 108 4.3.3 Aug 2014					X	X	X

Properties and Specifications

Property	15	22	32	46	68	100	150
Grade	ISO 15	ISO 22	ISO 32	ISO 46	ISO 68	ISO 100	ISO 150
Brookfield Viscosity @ -20 C, mPa.s, ASTM D2983			1090	1870	3990	11240	34500
Brookfield Viscosity @ -30 C, mPa.s, ASTM D2983			3360	7060	16380	57800	
Brookfield Viscosity @ -40 C, mPa.s, ASTM D2983	2620	6390	14240	55770			
Copper Strip Corrosion, 3 h, 100 C, Rating, ASTM D130	1B	1B	1B	1B	1B	1B	1B
Density @ 15.6 C, kg/l, ASTM D4052	0.837	0.841	0.846	0.850	0.862	0.877	0.881
Dielectric Strength, kV, ASTM D877	45	54	49	41			
FZG Scuffing, Fail Stage, DIN 51354			12	12	12	12	12

Flash Point, Cleveland Open Cup, °C, ASTM D92	178	212	215	232	240	241	246
Foam, Sequence I, Stability, ml, ASTM D892	0	0	0	0	2	0	0
Foam, Sequence I, Tendency, ml, ASTM D892	20	20	20	20	20	20	20
Foam, Sequence II, Stability, ml, ASTM D892		0	0	0	0	0	0
Foam, Sequence II, Tendency, ml, ASTM D892	20	20	20	20	20	20	20
Foam, Sequence III, Stability, ml, ASTM D892	0	0	0	0	0	0	0
Foam, Sequence III, Tendency, ml, ASTM D892	20	20	20	20	20	20	20
Kinematic Viscosity @ 100 C, mm ² /s, ASTM D445	4.07	5.07	6.63	8.45	11.17	13	17.16
Kinematic Viscosity @ 40 C, mm ² /s, ASTM D445	15.8	22.4	32.7	45.6	68.4	99.8	155.6
Pour Point, °C, ASTM D97	-56	-52	-49	-43	-38	-34	-34
Shear Stability, %KV Loss, CEC L-45-A-99	5	5	5	7	11	7	7
Viscosity Index, ASTM D2270	168	164	164	164	156	127	120

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2020

Exxon Mobil Corporation

22777 Springwoods Village Parkway
Spring TX 77389

1-800-ASK MOBIL (275-6624)

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

Energy lives here™

[Privacy Policy](#) • [Terms & Conditions](#)

© Copyright 2003-2020 Exxon Mobil Corporation.
All Rights Reserved.